

# CRC Food Zone Silicone Sealant – Aluminum

Para obtener información adicional en Español, visite [www.crcindustries.com](http://www.crcindustries.com).

- QUICKLY SEALS, bonds, protects, insulates and waterproofs.
- CURES RAPIDLY at room temperature.
- BONDS SOLIDLY throughout a temperature range of -70°F to 400°F.
- RESISTS sagging and slumping when applied overhead or on sidewall joints.
- ADHERES to metal, glass, silicone resin, most types of wood, vulcanized silicone, rubber, natural and synthetic fiber ceramic, painted and many plastic surfaces.

## DIRECTIONS: Please read entire label before use.

1. Clean and dry all surfaces. Remove any oil and grease prior to application. Sealant adheres best to clean, unpainted surfaces.
2. Cut tip and attach nozzle. Cut nozzle at an angle to desired bead size.
3. Apply with a caulking gun, forcing sealant into the joint.
4. If further tooling is required, complete within 5 minutes. Remove excess sealant immediately with a dry paper towel.
5. Sealant “skins” in approximately 10 minutes, dries to the touch in one hour, and fully cures and bonds in 24 hours.
6. If gasket is not used in assembly, apply sealant to surface of one part and allow skin to form before assembling parts.
7. After sealant is completely cured, excess material can be removed by trimming with a sharp blade. Avoid undercutting the sealant.
8. If contents are not completely used, seal the nozzle with a suitable object (nail) for future use.
9. Not recommended for use involving continuous immersion in gasoline or head gasketing operations.

## Precautionary Statements

Use with adequate ventilation. Open doors and windows or use other means to ensure a fresh air supply during use and while product is drying. Store away from incompatible materials. Do not store container above 100 °F/38 °C. Dispose of contents/container in accordance with local/regional/national regulations.

## First Aid

Wash hands after handling.

Contains polydimethylsiloxane 70131-67-8, amorphous silica 7631-86-9, hydrotreated middle distillates 64742-46-7, aluminum 7429-90-5, iron oxide 1309-37-1, titanium dioxide 13463-67-7, and carbon black 1333-86-4. For additional information, consult SDS for this product.

**VOC Category:** Sealant or Caulking Compound **VOC Limit:** 3%

©2017 CRC Industries, Inc.  
885 Louis Dr., Warminster, PA 18974  
800-521-3168 (Technical Information)  
800-272-4620 (Customer Care)

17A  
Made in U.S.A.  
[www.crcindustries.com](http://www.crcindustries.com)



# Food Zone Silicone Sealant

**ALUMINUM**

**Certified for use  
on Food Equipment**

**NSF**

**Under NSF / ANSI #51**

**Meets FDA Reg 21  
CFR 177.2600**



No. 14088  
Item# 1004824

**10.1 fl oz (298 mL)**

**KEEP AWAY FROM CHILDREN.**  
Read warnings on back panel.

